

Technical Datasheet

ZOLTEK™ OX Yarns

DESCRIPTION

ZOLTEK OX yarns are spun yarns manufactured from ZOLTEK OX tow. ZOLTEK OX yarns are inherently fire resistant, thermally stable, electrically nonconductive and exhibit excellent resistance to chemicals and solvents. ZOLTEK OX yarns can be knit or woven and are used in high performance FR apparel, woven welding blankets, industrial fire-blocking layers, mechanical seals and gaskets, high temperature belting and can also be carbonized for use in carbon fiber composite end uses.



TYPICAL PROPERTIES

Worsted Count*	Plies	Denier (g/9000 m)	Decitex (g/10 km)	Yield (yds/lb)	Yield (m/kg)	Turns Per Inch & "Twist"
1/27	1	296	329	15,120	30,480	10.0 - "Z"
2/27	2	592	658	7,560	15,240	6.0 - "S"
1/10	1	801	890	5,600	11,289	6.0 - "Z" or "S"
2/10	2	1,603	1,781	2,800	5,645	5.0 - "S"
1/5	1	1,568	1,742	2,850	5,745	6.0 - "Z"
2/5	2	3,151	3,501	1,425	2,873	2.1 - "S"

*Custom yarn counts and plied yarns, up to 10 plies, are available.

FIBER PROPERTIES	STANDARD DENSITY	HIGH DENSITY
Density	1.37 g/cm ³ (0.0495 lb/in ³)	1.40 g/cm ³ (0.0506 lb/in ³)
Diameter	12.5 microns	
LOI	40%+	50%+
Color	Black	
Resistivity	8 x 10 ⁸ Ω cm	

The properties listed in this datasheet do not constitute any warranty or guarantee of values. This information should only be used for the purposes of material selection. Please contact us for more details.

ZOLTEK OX



Technical Datasheet

ZOLTEK™ OX Yarns

CHEMICAL COMPOSITION %	
Carbon Content	62
Nitrogen	21.5
Oxygen	12
Hydrogen	4.5
Sodium	<.1
Trace Metals	<.01

CHEMICAL RESISTANCE	
Strong Acids	Good
Weak Acids	Excellent
Strong Bases	Poor
Weak Bases	Good
Organic Solvents	Excellent

The properties listed in this datasheet do not constitute any warranty or guarantee of values. This information should only be used for the purposes of material selection. Please contact us for more details.

RECOMMENDED USE

For protective apparel, woven welding blankets, scrim fabrics, mechanical packings and gaskets and precursor for carbonized yarns and fabrics. After carbonization, the surface fibers extending in multiple directions make the product ideally suited for high performance carbon composite end uses.

TYPICAL PACKAGING

ZOLTEK OX Yarns are wound on 6” conical cones and packaged in plastic lined boxes.

CERTIFICATION

ZOLTEK OX yarns are manufactured in accordance with ZOLTEK’s written and published data. A Certificate of Conformance is provided with each shipment.

SAFETY

Obtain, read, and understand the Material Safety Data Sheet (SDS) before use of this or any other ZOLTEK product.

APPROVAL

ZOLTEK OX yarns meet the human-ecological requirements established by Oeko-Tex® Standard 100 for products used in direct contact with skin.



ZOLTEK OX

