TECHNICAL DATASHEET

ZOLTEK[™] OX KNIT AND SATIN WEAVE FABRICS

DESCRIPTION

ZOLTEK OX satin weaves and circular knits are produced from 100% ZOLTEK OX yarn. These fabrics are characterized by high LOI%, excellent stretch, no melt-no drip and a soft hand for apparel applications.

Recommended use: Protective apparel, furniture & bedding



MATERIAL OVERVIEW	SATIN WEAVE - SW08		KNIT FABRIC - KF07		
	SI	US	SI	US	
Areal Weight	471 g/m²	13.9 oz/yd ²	424 g/m ²	12.5 oz/yd ²	
Warp and Fill	126 x 126/10 cm	32 x 32/in	N/A	N/A	
Width	129 cm	51 in	66 cm unslit	26 in	
Roll Length	45 m	50 yds	35 m	39 yds	
Thickness	1.2 mm	0.047 in	1.4 mm	0.055 in	
Yarn Input	2/10 Worsted Count		2/10 Worsted Count		
Construction	8 Harness Satin		Single Knit Tubular		

FIBER PROPERTIES		CHEMICAL CO	MPOSITION (%)	CHEMICAL RESISTANCE	
Density	1.36 g/cc min.	Carbon Content	62	Strong Acids	Good
Diameter	12.5μ	Nitrogen	21.5	Weak Acids	Excellent
LOI	40%+	Oxygen	12	Strong Bases	Poor
Color	Black	Hydrogen	4.5	Weak Bases	Good
Resistivity	8x10 ⁸ ohms-cm	Sodium	< 0.1	Organic Solvents	Excellent
		Trace Metals	< 0.01		

The properties listed in this datasheet do not constitute any warranty or guarantee of values. This information should only be used for the purposes of material selection. Please contact us for more details.



ZOLTEK Corporation 3101 McKelvey Road | Bridgeton, MO 63044 P: 314-291-5110 | www.zoltek.com



ZOLTEK[™] OX KNIT AND SATIN WEAVE FABRICS

TYPICAL PACKAGING

ZOLTEK OX Satin Weave & Knit Fabrics are wound on cardboard tubes and sealed in plastic.

CERTIFICATION

ZOLTEK OX Satin Weave & Knit Fabrics are manufactured in accordance with ZOLTEK's written and published data. A Certificate of Conformance is provided with each shipment.

SAFETY

Obtain, read, and understand the Material Safety Data Sheet (SDS) before use of this or any other ZOLTEK product.



ZOLTEK Corporation 3101 McKelvey Road | Bridgeton, MO 63044 P: 314-291-5110 | www.zoltek.com

